

U.S. Patent Application Serial No. 10/524,417  
Amendment filed March 23, 2010  
Reply to OA dated November 25, 2009

**AMENDMENTS TO THE CLAIMS:**

Please cancel claims 4 and 5 without prejudice or disclaimer, and amend claims 1 and 6, as follows. This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

Claim 1 (Currently amended): A laminate consisting ~~essentially~~ of a heat ray reflection substrate having solar radiation reflectance of 55.3% or less and visible light reflectance of 10% or more to 53.4% or less, and a visible light absorbing film formed by a visible light absorbing ink having been coated on one side or both sides of said substrate, said ink containing fine particles which absorb visible-region light and transmit near-infrared-region light and infrared-region light, the laminate characterized in that:

the degree of reduction of visible light reflectance is 0.9 or less as defined by degree of reduction of visible light reflectance = [visible light reflectance (%) of the laminate after coating of the ink]/[visible light reflectance (%) of the substrate before coating of the ink]; and

the degree of reduction of solar radiation reflectance is 0.25 or more as defined by degree of reduction of solar radiation reflectance = [solar radiation reflectance (%) of the laminate after coating of the ink]/[solar radiation reflectance (%) of the substrate before coating of the ink]; [[and]]

said visible light absorbing ink contains at least one fine particles of a compound oxide selected from the group consisting of Cu-Fe-Mn, Cu-Cr, Cu-Cr-Mn, Cu-Cr-Mn-Ni, Cu-Cr-Fe and

U.S. Patent Application Serial No. 10/524,417  
Amendment filed March 23, 2010  
Reply to OA dated November 25, 2009

Co-Cr-Fe, ~~titanium black~~, titanium nitride, and titanium oxynitride, ~~a dark-colored azo pigment, a perylene black pigment, and an aniline black pigment~~, said fine particles having an average dispersed-particle diameter of 300 nm or less in the ink; and

the heat ray reflection substrate comprises: a semitransparent polyethylene terephthalate film having a surface which is uniformly vacuum-deposited with an aluminum thin film without any crevices; or a composite comprising the semitransparent polyethylene terephthalate film having a surface which is uniformly vacuum-deposited with an aluminum thin film without any crevices, and a glass plate.

Claim 2 (Previously presented): The laminate according to claim 1, wherein, as a haze value measured according to JIS K 7105, the laminate having the visible light absorbing film formed on one side or both sides of the heat ray reflection substrate has a haze value which has been made lower than the haze value of the substrate before formation of the visible light absorbing film, or the laminate having the visible light absorbing film formed on one side or both sides of the heat ray reflection substrate has a haze value which has been made higher than the haze value of the substrate before formation of the visible light absorbing film and its gain is +3% or less.

Claim 3 (Previously presented): The laminate according to claim 1, which has a value of 40 or less as chromaticness  $c^* = [(a^*)^2 + (b^*)^2]^{1/2}$  in the  $L^*a^*b^*$  color system.

U.S. Patent Application Serial No. **10/524,417**  
Amendment filed March 23, 2010  
Reply to OA dated November 25, 2009

Claims 4-5 (Canceled).

Claim 6 (Currently amended): A structural member having a visible light absorbing film, characterized in that the laminate according to claim 1, 2, or 3, ~~4 or 5~~ is incorporated directly or via an intervenient member or via a space.

Claim 7 (Canceled).

Claim 8 (Previously presented): The laminate according to claim 1, wherein said visible light absorbing ink contains as a binder component at least one inorganic high polymer, organic high polymer or inorganic-organic composite high polymer.